

Sportfloor Grip

Adhesion promoter for pre-finished sports wooden floors



Varnishes & Finishing

Two-component, water-based primer that can be used as an adhesion promoter before overcoating on pre-finished UV parquet for sports use. It guarantees the perfect adhesion of our Sportfloor series products on pre-finished sports wooden floors. It does not affect the final appearance of the finishing products used.

Sportfloor Grip

Technical data at 20 °C and 60% R.H.

Appearance	Comp. A – White liquid Comp. B – Transparent liquid
Use ratio	10:1 with hardener B Plus
Blend Density	1.030 kg/litre
pH	7.5
Pot-life	4 hours
Dust dry	20 minutes
Touch dry	1 hour
Overcoatable	Minimum 4 hours
Possible dilution	Rallenty (max 5%) or water
Yield	14 – 16 m ² /litre
VOCs	100 g/litre, cat A/j (WB), limit 140 g/litre (2004/42/EC)
Application temperature	From +5 to +35 °C
Tool cleaning	Clean the roller immediately after use with water and neutral soap using a roller wringer until the roller itself is no longer soaked in opalescent liquid; if possible, rinse again with clean water. Store the rollers in suitably diluted Soluzione di Lavaggio S/28; rinse with clean water before reusing them.
Storage	12 months in original sealed packages – Frost sensitive
Packaging	Plastic cans of 5 + 0.5 litres



Certifications



Instructions for use

The prefinished surface must be clean, dry and completely free from wax residues or other maintenance products. If necessary, wash the floor with Sportfloor Cleaner.

Before applying Sportfloor Grip, the surface of the prefinished floor must be sanded homogeneously with a new mesh (180 – 220 grit) and the dust must be completely removed.

Shake component A well and mix component B in the exact use ratio (10:1), incorporating it slowly and stirring during the operation.

Apply a coat of Sportfloor Grip with a roller or brush, taking care to treat the entire surface uniformly; to obtain the best performance results, the applied layer should be very thin.

Wait at least 4 hours before applying the finish (Sportfloor Skate or Sportfloor Finish) or coloring (Sportfloor Color).

Sportfloor Grip must not be sanded!

For roller application, we recommend the use of microfibre rollers with a pile of 4 – 6 mm.

Notes

Frost sensitive.

Do not mix with other lacquers.

Avoid air drafts.

Turn off the heating especially if underfloor.

Although the A+B mixture can be kept fluid for a few hours, the application must be carried out no later than the indicated pot-life (4 hours) to obtain a continuous and homogeneous film.

The effectiveness of the promoter has been tested on countless prefinished floors; however, the variety of industrial finishing treatments is such that we recommend to always carry out preventive adhesion tests (wait at least a week for the complete development of the anchoring properties).

Safety standards

PRODUCT FOR PROFESSIONAL USE. Strictly comply with the labelling and consult the safety data sheets before using the product.

Disposal

Dispose of unused product and empty packaging in accordance with local legislation.



Varnishes &
Finishing

Sportfloor Grip



Certifications



The advice in this technical data sheet is given as an indication and does not in any way engage our responsibility since the methods and conditions of use of the product are beyond our control. We recommend checking the effective suitability for the intended use.
Rev 02 – 08/09/2021. This data sheet replaces the previous one.